


This is a standard Extension test

### Specimen 1 to 1



	Operator Name	Start Date	Area (cm <sup>2</sup> )	Length (mm)
1	David Chen	10/26/2012 4:20 PM	0.01000	110.00000
Mean			0.01000	110.00000
Standard Deviation			-----	-----

	Rate 1 (mm/min)	Load at Preset Point (Strain 1 10 %) (kN)	Tensile stress at Preset Point (Strain 1 10 %) (MPa)	Time at Preset Point (Strain 1 10 %) (sec)
1	110.00000	-----	-----	-----
Mean	110.00000	-----	-----	-----
Standard Deviation	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Load at Break (Standard) (kN)	Extension at Break (Standard) (mm)	Energy at Break (Standard) (kJ)
1	-----	-----	-----	-----
Mean	-----	-----	-----	-----
Standard Deviation	-----	-----	-----	-----