


This is a standard Extension test

Specimen 1 to 1



	Operator Name	Start Date	Area (cm ²)	Length (mm)
1	jimmy	12/14/2012 4:06 PM	0.28653	42.60000
Mean			0.28653	42.60000
Standard Deviation			-----	-----

	Rate 1 (mm/min)	Load at Preset Point (Strain 1 10 %) (kN)	Tensile stress at Preset Point (Strain 1 10 %) (MPa)	Time at Preset Point (Strain 1 10 %) (sec)
1	10.00000	-----	-----	-----
Mean	10.00000	-----	-----	-----
Standard Deviation	-----	-----	-----	-----

	Modulus (Automatic) (MPa)	Load at Break (Standard) (kN)	Extension at Break (Standard) (mm)	Energy at Break (Standard) (kJ)
1	773.66975	0.57726	13.04022	0.00963
Mean	773.66975	0.57726	13.04022	0.00963
Standard Deviation	-----	-----	-----	-----